

Report No: MAT:Concrete Sand

Material Test Report

Client: Miscellaneous

Project: Miscellaneous

Date of Issue:
THIS DOCUMENT SHALL NOT BE REPRODUCED EXCEPT IN FULL


Sample Details

Sample ID: Concrete Sand
Field Sample: CS11001
Date Sampled: 29/09/2011
Source: Stockpile
Material: Concrete Sand
Specification: PSD and finer 75u by washing - concrete
Sampling Method: Hand Sampling [AS1141.3.1]
Location:
GPS Easting:
GPS Northing:

Other Test Results

Description	Method	Result	Limits
Clay and Fine Silt (%)	AS 1141.33	3	≤8
Moisture Content (%)	AS 1289.2.1.1	2.0	
Organic Impurities	AS 1141.34	Pass	
Method of Assessment	Lovibond Colorimeter		

Particle Size Distribution



Method: AS 1141.11.1

Drying by: Hotplate

Note: Sample Washed

Sieve Size	% Passing	Limits
2.36mm	100	98 – 100
1.18mm	100	95 – 100
600µm	82	80 – 95
425µm	52	50 – 65
300µm	22	17 – 30
150µm	1	0 – 4
75µm	0	0 – 1

Comments

N/A